

# Perlast® G75B

Exceptional chemically resistant perfluoroelastomer

## PERLAST®

### Description

Perlast® G75B offers a unique blend of excellent chemical resistance, mechanical properties and high temperature stability, simultaneously extending the operating limits in all three aspects.

Perlast® G75B has been specially formulated to provide increased acid resistance by eliminating fillers that are prone to acid attack and optimising the polymer structure. In addition, this perfluoroelastomer has low permeability and as a result, it is less prone to swelling, leading to extended in-service performance in, for example, valves, pumps and mechanical seals.

A high modulus makes Perlast® G75B resistant to extrusion and ideal for use in medium-high pressure applications. In addition, the low cumulative compression set provides a high mean-time between maintenance cycles in hot chemically aggressive environments.

Perlast® G75B is suitable for both dynamic and static applications and can be fully moulded into O-rings (any size up to 2m/6.5ft internal diameter) and custom shapes.

### Key Attributes

- ▶ Excellent chemical resistance to a wide range of chemicals
- ▶ Exceptional acid and amine resistance
- ▶ Superior mechanical properties
- ▶ Long-term sealing efficiency at high temperature
- ▶ Extremely low out-gassing properties
- ▶ Good steam resistance (ASME BPE 2000)
- ▶ Less than 2% swell in MIL-L-23699C jet oil after 336 hours at 200°C

### Typical Applications

<b>Aerospace</b> –	Inter-stage seal assemblies (static O-rings)
<b>Chemical Processing</b> –	Pumps Valves Mechanical seals
<b>Diesel</b> –	Pre-heat chambers Exhaust valve seats
<b>Semiconductor</b> –	Gas abatement systems (static) High temperature environments
<b>Oil &amp; Gas</b> –	High temperature down-hole environments Electrical bulkhead feed-throughs

### Other materials in this range

Perlast® G75TX (black high temperature grade)

Perlast® G75M (black multi-purpose perfluoroelastomer)



### Typical Material Properties

Property	Test method	Value
Material Type	ASTM D1418	FFKM
Colour		Black
Hardness (Shore A)	ASTM D2240	85
Tensile Strength (MPa)	ASTM D412	18.0
Elongation at break (%)	ASTM D412	125
50% Modulus (MPa)	ASTM D412	10.0
100% Modulus (MPa)		16.0
Compression Set (%): 72 h @ 200°C (392°F)	ASTM D395B	18
Minimum Operating Temperature		-15°C (+5°F)
Maximum Operating Temperature	*	+325°C (+617°F)
Continuous Use Temperature	**	+275°C (+527°F)

\* and \*\* PPE proprietary test methods

**SPECIAL NOTE:** This information is to the best of our knowledge accurate and reliable. However, PPE Ltd makes no warranty, expressed or implied that parts manufactured from this material will perform satisfactorily in the customer's application. It is the customer's responsibility to evaluate parts prior to use, especially in applications where their failure may result in injury and/or damage. It should also be noted that all elastomeric parts have a finite life, therefore a regular program of inspection and replacement is strongly recommended. In non-black grades of elastomer, it is possible to observe slight variations in colour. This is normal and is inherent in the part; it is not indicative of foreign matter. These colour variations are not expected to adversely affect the performance of the part. The material properties above should not be used for specification purposes.

Perlast® is a registered trademark of Precision Polymer Engineering Limited.



© Copyright Precision Polymer Engineering Ltd | Issue 4, Revision 0

Europe: +44 (0) 1254 295400 | USA: +1 979 353 7350 | Email: prepol.sales@idexcorp.com | www.prepol.com